


(AK)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 156 084 A2

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
21.11.2001 Bulletin 2001/47

(51) Int Cl.7: C09B 23/14, C09B 23/10,
G11B 7/24

(21) Application number: 01302847.7

(22) Date of filing: 27.03.2001

(84) Designated Contracting States:

AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR

Designated Extension States:

AL LT LV MK RO SI

- Huh, Young-jae
Seongnam-city, Kyungki-do (KR)
- Lee, Kyu-youn
Seocho-gu, Seoul (KR)

(30) Priority: 17.05.2000 KR 2647000004

(71) Applicant: SAMSUNG ELECTRONICS CO., LTD.
Suwon-City, Kyungki-do (KR)


(74) Representative: Kyle, Diana
Elkington and Fife
Prospect House
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(72) Inventors:

- Je, Jong-tae
Gangnam-gu, Seoul (KR)

(54) Hemicyanine dyes and optical recording media using the same

(57) A hemicyanine dye having formula (1) and an optical recording medium using the hemicyanine dye as an optical recording medium are provided:



...(1)

where Z is a benzene ring, naphthalene ring or anthracene ring; X_1 is S, O, Se, NR or $C(CH_3)_2$, where R is hydrogen or an alkyl group of 1 to 5 carbon atoms; R_1 is hydrogen, a halogen atom, an alkyl group of 1 to 3 carbon atoms, a nitro group, an alkoxy group of 1 to 3 carbon atoms or an amine group; each of R_2 and R_4 is an alkyl group of 1 to 5 carbon atoms; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; Y is Cl, Br, I, ClO_4 , BF_4 , BrO_4 , PF_6 , CH_3SO_3 , CF_3SO_3 , $4-CH_3C_6H_4SO_3$, $C_6H_5SO_3$, $6-SO_3C_{10}H_6SO_3$ or HSO_4 ; and n is an integer of 0-2. The hemicyanine dye having formula (1) above is easy to synthesize with high yield. Thus, use of the hemicyanine dye as an optical recording material in manufacturing optical recording media can reduce the manufacturing cost.

EP 1 156 084 A2

Description

[0001] The present invention relates to hemicyanine dyes and optical recording media formed using the same, and more particularly, to hemicyanine dyes, and a write once read many (WORM) type optical recording medium capable of recording and reproducing information with radiation of laser, which employs a hemicyanine dye as an optical recording material.

[0002] Optical recording media have a smaller recording area per recording unit than conventional magnetic recording media, so that use of the optical recording media as a high density recording medium is extensively increasing. Optical recording media are classified into a read only memory (ROM) type for only reading recorded information, a write once read many (WORM) type which allows only one writing, and an erasable type which allows erasing of recorded information and rewriting.

[0003] WORM type and erasable type optical recording media reproduce information by detecting variations in the reflectivity caused by physical deformation and changes in optical characteristics, and phase and magnetic properties of a recording layer before and after the recording.

[0004] A compact disk recordable (CD-R) is widely known as a WORM type optical recording medium. In addition, a variety of optical recording materials, which ensure easy manufacture of such a recording medium with improved properties, have been suggested and some of them are in use. Disclosed optical recording materials for CD-Rs include a cyanine dye (Japanese Patent Publication No. sho 58-125246), a phthalocyanine dye (European Patent No. 676,751), an azo dye (US Patent No. 5,441,844), a dye of double salt (US Patent No. 4,626,490) and a dye of azo-metal complex (US Patent No. 5 272,047).

[0005] Recently, with increased amount of information, a digital versatile disk recordable (DVD-R) with increased information storing capability has been suggested. The DVD-R adopts a red diode laser having a wavelength of 630-670 nm, as a light source, and has reduced pit size and track interval, so that its information storing capacity is 6-8 times increased with respect to CD-Rs. Examples of the optical recording media for DVD-Rs include a cyanine dye (Japanese Patent Publication Nos. hei 10-149583 and hei 9-208560), a dye of azo-metal complex (Japanese Patent Publication Nos. hei 10-157293 and hei 9-157301), and the like.

[0006] The erasable type optical recording media record and reproduce information based on the changes in phase of metal alloy. Recent approaches to the erasable optical recording media have been focused on use of the photochromic phenomenon of organic substances. Organic substances with the photochromic phenomenon include spiropyran, fulgide, dihydropyrene, thioindigo, bipyridine, aziridine, polynuclear aromatics, azobenzene, salicylideneaniline, xanthene, oxazine and the like. In particular, spiropyran, which is a typical organic substance having the photochromic phenomenon, has both colored and clear structures. The clear structure is changed into a colored structure by radiation of ultraviolet (UV) rays, and the colored structure is changed into a colorless structure by radiation of visible rays. In other words, the two structures can be reversed depending on the wavelength of radiated light.

[0007] Spiropyran is suitable as a recording material used for erasable type optical recording media, due to its reversible structure described previously, but not for WORM type optical recording media. For this reason, application of the photochromic substance in manufacturing WORM type optical recording media rarely appears in the related field.


[0008] According to the present invention, spiropyran, a typical photochromic substance, is adopted as a material for WORM type optical recording media, by blocking the changing of the colored structure to the clear structure by radiation of light or heat, using that the colored structure has a strong absorption band in the visible wavelength range.

[0009] In order to prevent the reversible changing of the structures, an electron donor having a stronger electron donating ability than that of a hydroxy group is further introduced into its structure, or the hydroxy group is eliminated from the structure, which hinders the reaction for the clear structure. The modified spiropyran has optical characteristics similar to those of cyanine dye, excellent solubility in organic solvent, and a decomposition temperature of 210-260°C. Also, the synthesis pathway of the modified spiropyran is simpler than the original spiropyran with high yield. Thus, the modified spiropyran can be effectively used as an inexpensive optical recording material.

[0010] To solve the above problems, it is a first objective of the present invention to provide a novel hemicyanine dye which is easy to synthesize with high yield.


[0011] A second objective of the present invention is to provide a write once read many (WORM) type optical recording medium, which can be manufactured at a reduced cost, by using the hemicyanine dye as an optical recording material.

[0012] The first objective of the present invention is achieved by a hemocyanine dye having formula (1):



where Z is a benzene ring, naphthalene ring or anthracene ring; X_1 is S, O, Se, NR or $C(CH_3)_2$, where R is hydrogen or an alkyl group of 1 to 5 carbon atoms; R_1 is hydrogen, a halogen atom, an alkyl group of 1 to 3 carbon atoms, a nitro group, an alkoxy group of 1 to 3 carbon atoms or an amine group; each of R_2 and R_4 is an alkyl group of 1 to 5 carbon atoms; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; Y is Cl, Br, I, ClO_4 , BF_4 , BrO_4 , PF_6 , CH_3SO_3 , CF_3SO_3 , $4-CH_3C_6H_4SO_3$, $C_6H_5SO_3$, $6-SO_3C_{10}H_6SO_3$ or HSO_4 ; and n is an integer of 0-2.


[0013] The second objective of the present invention is achieved by an optical recording medium comprising a transparent substrate with grooves, a recording layer including a laser absorptive dye, formed over the transparent substrate, and a reflective layer and a protective layer formed over the recording layer, wherein the dye of the recording layer is a hemicyanine dye having formula (1):




where Z is a benzene ring, naphthalene ring or anthracene ring; X_1 is S, O, Se, NR or $C(CH_3)_2$, where R is hydrogen or an alkyl group of 1 to 5 carbon atoms; R_1 is hydrogen, halogen atoms, an alkyl group of 1 to 3 carbon atoms, a nitro group, an alkoxy group of 1 to 3 carbon atoms or an amine group; each of R_2 and R_4 is an alkyl group of 1 to 5 carbon atoms; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; Y is Cl, Br, I, ClO_4 , BF_4 , BrO_4 , PF_6 , CH_3SO_3 , CF_3SO_3 , $4-CH_3C_6H_4SO_3$, $C_6H_5SO_3$, $6-SO_3C_{10}H_6SO_3$ or HSO_4 ; and n is an integer of 0-2.

[0014] In a hemicyanine dye having formula (1) according to the present invention, Z is a benzene ring, a naphthalene ring or an anthracene ring.


[0015] Apparently, in formula (1), the portion (I) including the ring indicated by Z represents a condensed ring formed by covalently coupling at least two atoms between an octagonal ring compound selected from the group consisting of thiazole ring, oxazole ring and imidazole ring, and one of the benzene ring, naphthalene ring and anthracene ring. The concrete examples of the portion (I) are as follows.






where Z is a benzene ring, naphthalene ring or anthracene ring; X_1 is S, O, Se, NR (where R is hydrogen or an alkyl group of 1 to 5 carbon atoms) or $C(CH_3)_2$; R_1 is hydrogen, halogen atoms, an alkyl group of 1 to 3 carbon atoms, a nitro group, an alkoxy group of 1 to 3 carbon atoms or an amine group; each of R_2 and R_4 is an alkyl group of 1 to 5 carbon atoms; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; Y is Cl, Br, I, ClO_4 , BF_4 , BrO_4 , PF_6 , CH_3SO_3 , CF_3SO_3 , $4-CH_3C_6H_4SO_3$, $C_6H_5SO_3$, $6-SO_3C_{10}H_6SO_3$ or HSO_4 ; and n is an integer of 0-2.

[0016] Preferably, the hemicyanine dye having formula (1) is a compound having formula (2) or (3) below:





... (2)

where R_1 is H, NO_2 or Cl; R_2 is CH_3 , C_2H_5 , C_3H_7 or C_4H_9 ; X_1 is $C(CH_3)_2$ or S; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; R_4 is C_2H_5 , C_3H_7 or C_4H_9 ; and Y is ClO_4 , BF_4 , PF_6 , I, Br or Cl, and



where X_1 is $C(CH_3)_2$; R_2 is CH_3 , C_2H_5 , C_3H_7 or C_4H_9 ; R_3 is H or OH; R_4 is C_2H_5 , C_3H_7 or C_4H_9 ; and Y is ClO_4 , BF_4 , PF_6 , I, Br or Cl.

[0017] The synthesis of the novel hemicyanine dye having formula (1) according to the present invention will be described with reference to the following reaction scheme (I). The hemicyanine dye having formula (1) above is obtained by condensing compounds (A) with compound (B). Compound (A) can be derived by the following process illustrated in reaction scheme (I).



[0018] Compound (A) is obtained by N-alkylation of compound (A-1) with excess halogen compound, for example, iodomethane, iodoethane, iodopropane, iodobutane.

[0019] An optical recording medium according to the present invention, which is manufactured using the hemicyanine dye having formula (1) above as an optical recording material, is a write once read many (WORM) type optical recording medium which records and reproduces information using a laser beam, and particularly, is a DVD-R using a short wavelength laser beam as a light source.

[0020] The present invention is described in more detail with reference to the attached drawing in which:

[0021] FIG. 1 is a sectional view illustrating the structure of layers stacked in an optical recording medium according to a preferred embodiment of the present invention. Referring to FIG. 1, a recording layer 11, which contains the hemicyanine dye having formula (1) above used as an optical recording medium, a reflective layer 12 and a protective layer 13 are deposited in succession over a semiconductor substrate 10.

[0022] For certain cases, a dummy substrate 15 can be attached to the optical recording medium using an adhesive layer 14. Alternatively, the optical recording medium of FIG. 1 can be combined with another optical recording medium having the same or different structure as or from that of FIG. 1. A material used for the adhesive layer 14 may be a ultraviolet (UV) curable resin, or a cationic curable resin. Also, such combination with an adhesive layer can be performed using a two-sided adhesive sheet, or by a hot-melting, spin coating, dispensing (extrusion), screen printing, or roll-coat method.

[0023] Preferably, the substrate 10 is formed of a material, which is transparent to a laser beam and easy to swell by heat, and has a strong impact resistance. Suitable materials for the substrate 10, which meet the requirements, include polycarbonate, polymethacrylate, epoxy resin, polyester resin and polyolefin resin. These materials used for the substrate 10 have a thermal deformation temperature in the range of 80-200°C, but preferably in the range of

100-200°C.

[0024] Pregrooves for guiding an incident laser beam during recording or reproducing are formed on the surface of the substrate 10. Preferably, the pregrooves have a depth of 80-250 nm, and a width of 200-500 μm . Preferably, the substrate 10 has a transmittance of 60-99% more preferably 70-99%, with about 90% being preferred, and a thickness of 0.01-10 mm. If the transmittance or thickness of the substrate is beyond the above range, the optical recording medium characteristics are unfavorable.

[0025] The recording layer 11 includes an organic dye, which is physically deformed and decomposed by a recording laser beam. In the present invention, the recording layer 11 may include at least one hemicyanine dye having formula (1). As needed, the recording layer 11 can further include a singlet oxygen quencher, a light absorptive material and a radical scavenger. Preferably, the optical recording material used in the recording layer 11 has a complex refractive index, including a real part coefficient n of 1.5-2.8 and an imaginary part coefficient k of 0.01-0.4 in the wavelength range for recording and reproduction. More preferably, the optical recording material has a refractive index of 1.8-2.3 in a wavelength range of 400-700 nm. Preferably, the optical recording medium has a maximum absorption wavelength of 350-650 nm. If the complex refractive index and the maximum absorption wavelength of the optical recording material are beyond the above ranges, recording and reproducing characteristics in terms of recording sensitivity, push-pull, tracking and modulation factor are unfavorable.

[0026] The recording layer 11 is formed by spin coating a composition over a substrate. The composition for the recording layer 11 is obtained by dissolving 0.5-10% by weight hemicyanine dye having formula (1) in a solvent of 90-99.5% by weight based on the total weight of the composition. Any solvent capable of dissolving the hemicyanine dye without causing defects on the substrate can be used without limitations.

[0027] Preferably, the reflective layer 12, which ensures high reflectivity for recording or reproducing, is formed of a metal having a high reflectivity as well as a high thermal conductivity, such that the reflective layer 12 is not susceptible to deform. Suitable metals used for the reflective layer 12 include gold (Au), aluminum (Al), silver (Ag), copper (Cu), palladium (Pd), platinum (Pt), titanium (Ti), tantalum (Ta), chromium (Cr), nickel (Ni) or an alloy of these metals. Preferably, the reflective layer 12 has a thickness of 500-2500 Å. The reflective layer 12 may be formed by vacuum deposition, E-beam or sputtering.


[0028] In the present invention, the protective layer 13 serves to protect other constituents layers, and in particular, the reflective layer 12 of the optical recording medium. The protective layer 13 is formed by a common method. For example, a transparent UV curable material with strong impact resistance, such as epoxy or acrylate UV curable resin is spin-coated over the reflective layer 12, and then cured by radiation of UV rays.

[0029] The present invention will be described in greater detail by means of the following examples. The following examples are for illustrative purposes and are not intended to limit the scope of the invention.

Example 1

[0030] 2-Methylene-1,3,3-trimethylindoline was dissolved in ethyl acetate at room temperature, and HClO_4 solution was dropwise added to the mixture. The precipitate was filtered from the reaction mixture, and washed with ethyl acetate several times to obtain 1,2,3,3-tetramethylpseudoindolium perchlorate.

[0031] 1.2 Equivalents 2-hydroxy-4-diethylamino-benzaldehyde, and 1 equivalent 1,2,3,3-tetramethylpseudoindolium perchlorate were dissolved in ethanol, and 1 drop of piperidine was added to the mixture. Then, the reaction mixture was reacted under reflux for 5 hours and evaporated under vacuum to remove the solvent. Then, excess ethyl acetate was added to the resultant mixture, so that violet powder was precipitated. The precipitate was washed with ethyl acetate several times, so that dye D1 of violet color having the following formula was obtained with a yield of 95%.



[0032] NMR (1H, DMSO): 1.18 (t, 6H), 1.70 (s, 6H), 3.50 (q, 4H), 3.84 (s, 3H), 6.24 (s, 1H), 6.52 (d, 1H), 7.16 (d, 1H), 7.42 (t, 1H), 7.52 (t, 1H), 7.60 (d, 1H), 7.70 (d, 1H), 7.93 (d, 1H), 8.40 (d, 1H)

[0033] 0.3g of dye D1 was dissolved in 10 ml tetrafluoropropanol, and spin-coated over a substrate to form a dye thin film. The absorption spectrum of the obtained thin film was observed with a UV-VIS-NIR spectrophotometer (UV-3101PC, Shimadzu Co.) to detect the maximum absorption peak (λ_{max}). The obtained maximum absorption wavelength (λ_{max}), the melting temperature (T_m) and the decomposition temperature (T_d) of dye D1 are shown in Table 1.

[0034] 0.30 g of dye D1 and 0.04 g phenylamine series stabilizer (IRG022, Nippon Kayaku Co., Ltd) were dissolved in 10 ml tetrafluoropropane, and stirred at room temperature for 5 hours. The mixture was filtered with a Teflon filter (having 0.2 μm pore width) and spin-coated over a substrate to form a dye layer. The substrate was a polycarbonate substrate with 0.6 mm thickness having pregrooves with 150 nm depth, 300 nm width and 800 nm track pitch.


[0035] The substrate having the dye layer was dried in a vacuum oven set at 40°C for 12 hours. Then, silver (Ag) was deposited over the dye layer to form a reflective layer with a thickness of 100 nm. An acrylic UV curable resin was spin-coated over the reflective layer and then cured by radiation of UV rays to form a protective layer. The resultant substrate was combined with a dummy disk, thereby completing an optical, disk.

[0036] Characteristics of the obtained optical disk was evaluated by a DVD-R recorder (DVDR-S101, Pioneer), a dynamic characteristic evaluator (DDU-1000, Pulstec) equipped with a laser diode (LD, Nichia, Japan) having a peak wavelength of 630 nm or 650 nm, and a DVD player (DVD909, Samsung, Korea). Characteristics of the optical disk before recording were evaluated using the evaluator equipped with 635 nm LD. The results are shown in Table 1. In Table 1, Rtop indicates the maximum reflectivity, jitter indicates variations of reproduction signals, which is a signal uniformity index, I14/I14H indicates the modulated amplitude of recorded signals.

Examples 2 through 42


[0037] Dyes D2 through D42 were synthesized and optical disks were manufactured using each of the dyes D2 through 42, in the same manner as in Example 1. The results are shown in Table 1.

< Dye D2 >




[0038] NMR (1H, DMSO): 1.20 (t, 6H), 1.72 (s, 6H), 3.52 (q, 4H), 3.80 (s, 3H), 6.24 (s, 1H), 6.54 (d, 1H), 7.12 (d, 1H), 7.58 (d, 1H), 7.62 (d, 1H), 7.88 (s, 1H), 7.94 (d, 1H), 8.40 (d, 1H)

< Dye D3 >




[0039] NMR (1H, DMSO): 1.20 (t, 6H), 1.72 (s, 6H), 3.52 (q, 4H), 3.80 (s, 3H), 6.24 (s, 1H), 6.54 (d, 1H), 7.12 (d, 1H), 7.58 (d, 1H), 7.62 (d, 1H), 7.88 (s, 1H), 7.94 (d, 1H), 8.40 (d, 1H)

< Dye D4 >




[0040] NMR (1H, DMSO): 1.20 (t, 6H), 1.72 (s, 6H), 3.52 (q, 4H), 3.80 (s, 3H), 6.24 (s, 1H), 6.54 (d, 1H), 7.12 (d, 1H), 7.58 (d, 1H), 7.62 (d, 1H), 7.88 (s, 1H), 7.94 (d, 1H), 8.40 (d, 1H)

< Dye D5 >




[0041] NMR (1H, DMSO): 1.20 (t, 6H), 1.73 (s, 6H), 3.54 (q, 4H), 3.80 (s, 3H), 6.26 (s, 1H), 6.64 (d, 1H), 7.10 (d, 1H), 7.72 (d, 1H), 8.02 (d, 1H), 8.40 (d, 1H), 8.48 (d, 1H), 8.62 (s, 1H)

< Dye D6 >




[0042] NMR (1H, DMSO): 1.20 (t, 6H), 1.73 (s, 6H), 3.54 (q, 4H), 3.80 (s, 3H), 6.26 (s, 1H), 6.64 (d, 1H), 7.10 (d, 1H), 7.72 (d, 1H), 8.02 (d, 1H), 8.40 (d, 1H), 8.48 (d, 1H), 8.62 (s, 1H)

< Dye D7 >




[0043] NMR (1H, DMSO): 1.20 (t, 6H), 1.73 (s, 6H), 3.54 (q, 4H), 3.80 (s, 3H), 6.26 (s, 1H), 6.64 (d, 1H), 7.10 (d, 1H), 7.72 (d, 1H), 8.02 (d, 1H), 8.40 (d, 1H), 8.48 (d, 1H), 8.62 (s, 1H)

< Dye D8 >




[0044] NMR (1H, DMSO): 1.20 (t, 6H), 1.73 (s, 6H), 3.54 (q, 4H), 3.80 (s, 3H), 6.26 (s, 1H), 6.64 (d, 1H), 7.10 (d, 1H), 7.72 (d, 1H), 8.02 (d, 1H), 8.40 (d, 1H), 8.48 (d, 1H), 8.62 (s, 1H)

< Dye D9 >




[0045] NMR (1H, DMSO): 1.24 (t, 6H), 1.80 (s, 6H), 3.60 (q, 4H), 4.00 (s, 3H), 6.94 (d, 2H), 7.26 (d, 1H), 7.52 (t, 1H), 7.60 (t, 1H), 7.74 (d, 1H), 7.82 (d, 1H), 8.08 (d, 2H), 8.36 (d, 1H)

< Dye D10 >




[0046] NMR (1H, DMSO): 1.24 (t, 6H), 1.44 (t, 3H), 1.80 (s, 6H), 3.62 (q, 4H), 4.58 (q, 2H), 6.92 (d, 2H), 7.26 (d, 1H), 7.54 (t, 1H), 7.60 (t, 1H), 7.76 (d, 1H), 7.82 (d, 1H), 8.12 (d, 1H), 8.38 (d, 1H)

< Dye D11 >




[0047] NMR (1H, DMSO): 0.99 (t, 3H), 1.24 (t, 6H), 1.48 (m, 2H), 1.82 (s, 6H), 3.62 (q, 4H), 6.94 (d, 2H), 7.26 (d, 1H), 7.52 (t, 1H), 7.60 (t, 1H), 7.76 (d, 1H), 7.82 (d, 1H), 8.12 (d, 2H), 8.38 (d, 1H)

< Dye D12 >




[0048] NMR (1H, DMSO): 1.44 (t, 3H), 1.82 (s, 6H), 3.24 (s, 6H), 4.60 (q, 2H), 6.94 (d, 2H), 7.32 (d, 1H), 7.54 (t, 1H), 7.60 (t, 1H), 7.78 (d, 1H), 7.84 (d, 1H), 8.18 (d, 2H), 8.40 (d, 1H)

< Dye D13 >




[0049] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.96 (s, 3H), 6.86 (d, 2H), 7.20 (d, 1H), 7.46 (t, 1H), 7.56 (t, 1H), 7.68 (d, 1H), 7.76 (d, 1H), 8.04 (d, 2H), 8.26 (d, 1H)

< Dye D14 >




[0050] NMR (1H, DMSO): 1.24 (t, 6H), 1.44 (t, 3H), 1.80 (s, 6H), 3.62 (q, 4H), 4.58 (q, 2H), 6.92 (d, 2H), 7.26 (d, 1H), 7.54 (t, 1H), 7.60 (t, 1H), 7.76 (d, 1H), 7.82 (d, 1H), 8.12 (d, 1H), 8.38 (d, 1H)

< Dye D15 >




[0051] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.92 (s, 3H), 6.88 (d, 1H), 7.18 (d, 1H), 7.60 (d, 1H), 7.68 (d, 1H), 7.92 (s, 1H), 8.16 (d, 1H), 8.30 (d, 1H)

< Dye D16 >




[0052] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.92 (s, 3H), 6.88 (d, 1H), 7.18 (d, 1H), 7.60 (d, 1H), 7.68 (d, 1H), 7.92 (s, 1H), 8.16 (d, 1H), 8.30 (d, 1H)

< Dye D17 >




[0053] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.92 (s, 3H), 6.88 (d, 1H), 7.18 (d, 1H), 7.60 (d, 1H), 7.68 (d, 1H), 7.92 (s, 1H), 8.16 (d, 1H), 8.30 (d, 1H)

< Dye D18 >




[0054] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.92 (s, 3H), 6.88 (d, 1H), 7.18 (d, 1H), 7.60 (d, 1H), 7.68 (d, 1H), 7.92 (s, 1H), 8.16 (d, 1H), 8.30 (d, 1H)

< Dye D19 >




[0055] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.92 (s, 3H), 6.88 (d, 1H), 7.18 (d, 1H), 7.60 (d, 1H), 7.68 (d, 1H), 7.92 (s, 1H), 8.16 (d, 1H), 8.30 (d, 1H)

< Dye D20 >




[0056] NMR (1H, DMSO): 1.18 (t, 6H), 1.74 (s, 6H), 3.54 (q, 4H), 3.92 (s, 3H), 6.88 (d, 1H), 7.18 (d, 1H), 7.60 (d, 1H), 7.68 (d, 1H), 7.92 (s, 1H), 8.16 (d, 1H), 8.30 (d, 1H)

< Dye D21 >




[0057] NMR (1H, DMSO): 1.00 (t, 6H), 1.44 (m, 4H), 1.64 (m, 4H), 1.80 (s, 6H), 3.58 (t, 4H), 3.98 (s, 3H), 6.94 (d, 2H), 7.24 (d, 1H), 7.66 (d, 1H), 7.76 (d, 1H), 8.02 (s, 1H), 8.10 (d, 2H), 8.38 (d, 1H)

< Dye D22 >




[0058] NMR (1H, DMSO): 1.82 (s, 6H), 3.24 (s, 6H), 3.92 (s, 3H), 6.96 (d, 2H), 7.24 (d, 1H), 7.82 (d, 1H), 8.14 (d, 2H), 8.42 (d, 1H), 8.44 (d, 1H), 8.70 (s, 1H)

< Dye D23 >




[0059] NMR (1H, DMSO): 1.22 (t, 6H), 1.82 (s, 6H), 3.62 (q, 4H), 3.92 (s, 3H), 6.96 (d, 2H), 7.20 (d, 1H), 7.80 (d, 1H), 8.14 (d, 2H), 8.40 (d, 1H), 8.42 (d, 1H), 8.70 (s, 1H)

< Dye D24 >




[0060] NMR (1H, DMSO): 1.22 (t, 6H), 1.82 (s, 6H), 3.62 (q, 4H), 3.92 (s, 3H), 6.96 (d, 2H), 7.20 (d, 1H), 7.80 (d, 1H), 8.14 (d, 2H), 8.40 (d, 1H), 8.42 (d, 1H), 8.70 (s, 1H)

< Dye D25 >




[0061] NMR (1H, DMSO): 0.94 (t, 6H), 1.28 (m, 4H), 1.60 (m, 4H), 1.80 (s, 6H), 3.56 (t, 4H), 3.92 (s, 3H), 6.92 (d, 2H), 7.20 (d, 1H), 7.80 (d, 1H), 8.12 (d, 2H), 8.40 (d, 1H), 8.39 (d, 1H), 8.68 (s, 1H)

< Dye D26 >




[0062] NMR (1H, DMSO): 2.06 (s, 6H), 3.22 (s, 6H), 4.16 (s, 3H), 6.94 (d, 2H), 7.36 (d, 1H), 7.72 (t, 1H), 7.82 (t, 1H), 8.02 (d, 1H), 8.14 (d, 2H), 8.22 (d, 1H), 8.28 (d, 1H), 8.42 (d, 1H), 8.46 (d, 1H)

< Dye D27 >




[0063] NMR (1H, DMSO): 2.06 (s, 6H), 3.22 (s, 6H), 4.16 (s, 3H), 6.94 (d, 2H), 7.36 (d, 1H), 7.72 (t, 1H), 7.82 (t, 1H), 8.02 (d, 1H), 8.14 (d, 2H), 8.22 (d, 1H), 8.28 (d, 1H), 8.42 (d, 1H), 8.46 (d, 1H)

< Dye D28 >




[0064] NMR (1H, DMSO): 1.18 (t, 6H), 1.96 (s, 6H), 3.50 (q, 4H), 3.96 (s, 3H), 6.26 (s, 1H), 6.52 (d, 1H), 7.20 (d, 1H), 7.60 (t, 1H), 7.72 (t, 1H), 7.92 (d, 1H), 7.98 (d, 1H), 8.12 (d, 1H), 8.18 (d, 1H), 8.34 (d, 1H), 8.52 (d, 1H)

< Dye D29 >




[0065] NMR (1H, DMSO): 1.18 (t, 6H), 1.96 (s, 6H), 3.50 (q, 4H), 3.96 (s, 3H), 6.26 (s, 1H), 6.52 (d, 1H), 7.20 (d, 1H), 7.60 (t, 1H), 7.72 (t, 1H), 7.92 (d, 1H), 7.98 (d, 1H), 8.12 (d, 1H), 8.18 (d, 1H), 8.34 (d, 1H), 8.52 (d, 1H)

< Dye D30 >




[0066] NMR (1H, DMSO): 1.00 (t, 3H), 1.40 (m, 2H), 1.64 (m, 2H), 1.80 (s, 6H), 3.55 (t, 2H), 4.13 (s, 3H), 6.91 (d, 2H), 7.30 (d, 1H), 7.79 (t, 1H), 7.84 (t, 1H), 8.01 (d, 1H), 8.14 (d, 2H), 8.20 (d, 1H), 8.26 (d, 1H), 8.36 (d, 1H), 8.42 (d, 1H)

< Dye D31 >




[0067] NMR (1H, DMSO): 1.51 (t, 3H), 2.06 (s, 6H), 3.35 (s, 6H), 4.73 (q, 2H), 6.95 (d, 2H), 7.36 (d, 1H), 7.73 (t, 1H), 7.83 (t, 1H), 8.04 (d, 1H), 8.16 (d, 2H), 8.22 (d, 1H), 8.28 (d, 1H), 8.42 (d, 1H), 8.48 (d, 1H)

< Dye D32 >




[0068] NMR (1H, DMSO): 1.80 (t, 6H), 1.94 (s, 6H), 3.48 (q, 4H), 3.98 (s, 3H), 6.24 (s, 1H), 6.54 (d, 1H), 7.22 (d, 1H), 7.60 (t, 1H), 7.72 (t, 1H), 7.92 (d, 1H), 7.98 (d, 1H), 8.14 (d, 1H), 8.18 (d, 1H), 8.36 (d, 1H), 8.52 (d, 1H)

< Dye D33 >




[0069] NMR (1H, DMSO): 1.08 (t, 6H), 1.51 (t, 3H), 2.06 (s, 6H), 3.48 (q, 4H), 4.73 (q, 2H), 6.95 (d, 2H), 7.36 (d, 1H), 7.73 (t, 1H), 7.83 (t, 1H), 8.04 (d, 1H), 8.16 (d, 2H), 8.22 (d, 1H), 8.28 (d, 1H), 8.42 (d, 1H), 8.48 (d, 1H)

< Dye D34 >




[0070] NMR (1H, DMSO): 1.16 (t, 6H), 1.40 (t, 3H), 3.44 (q, 4H), 4.72 (q, 2H), 6.22 (s, 1H), 6.44 (d, 1H), 7.46 (d, 1H), 7.64 (s, 1H), 7.74 (d, 1H), 7.86 (d, 1H), 8.06 (d, 1H), 8.18 (d, 1H), 8.22 (d, 1H)

< Dye D35 >




[0071] NMR (1H, DMSO): 0.94 (t, 3H), 1.16 (t, 6H), 1.26 (m, 2H), 1.80 (m, 2H), 3.44 (q, 4H), 4.66 (t, 2H), 6.22 (s, 1H), 6.46 (d, 1H), 7.48 (d, 1H), 7.63 (t, 1H), 7.72 (t, 1H), 7.80 (d, 1H), 8.04 (d, 1H), 8.12 (d, 1H), 8.20 (d, 1H)

< Dye D36 >




[0072] NMR (1H, DMSO): 1.02 (t, 3H), 1.16 (t, 6H), 1.86 (m, 2H), 3.44 (q, 4H), 4.76 (t, 2H), 6.84 (d, 2H), 7.48 (d, 1H), 7.66 (t, 1H), 7.76 (t, 1H), 7.90 (d, 1H), 8.06 (d, 1H), 8.16 (d, 1H), 8.28 (d, 1H)

< Dye D37 >




[0073] NMR (1H, DMSO): 1.02 (t, 3H), 1.08 (t, 6H), 1.86 (m, 2H), 3.54 (q, 4H), 4.76 (t, 2H), 6.84 (d, 2H), 7.48 (d, 1H), 7.66 (t, 1H), 7.76 (t, 1H), 7.90 (d, 1H), 8.06 (d, 1H), 8.16 (d, 1H), 8.28 (d, 1H)

< Dye D38 >




[0074] NMR (1H, DMSO): 0.92 (t, 3H), 1.16 (t, 6H), 1.44 (m, 2H), 1.80 (m, 1H), 3.52 (q, 4H), 4.80 (t, 2H), 6.84 (d, 2H), 7.56 (d, 1H), 7.66 (t, 1H), 7.76 (t, 1H), 7.90 (d, 2H), 8.06 (d, 1H), 8.12 (d, 1H), 8.30 (d, 1H)

< Dye D39 >




[0075] NMR (1H, DMSO): 1.16 (t, 6H), 1.42 (t, 3H), 3.52 (q, 4H), 3.82 (q, 2H), 6.84 (d, 2H), 7.60 (d, 1H), 7.68 (t, 1H), 7.78 (t, 1H), 7.92 (d, 2H), 8.08 (d, 1H), 8.12 (d, 1H), 8.28 (d, 1H)

< Dye D40 >




[0076] NMR (1H, DMSO): 1.48 (t, 3H), 3.18 (s, 6H), 4.88 (q, 2H), 6.88 (d, 2H), 7.66 (d, 1H), 7.74 (d, 1H), 7.84 (t, 1H), 8.00 (d, 2H), 8.14 (d, 1H), 8.18 (d, 1H), 8.38 (d, 1H)

< Dye D41 >



[0077] NMR (1H, DMSO): 1.22 (t, 6H), 1.74 (s, 6H), 2.48 (s, 3H), 3.60 (q, 4H), 4.00 (s, 3H), 6.76 (s, 1H), 6.88 (d, 1H), 7.28 (d, 1H), 7.66 (d, 1H), 7.80 (d, 1H), 7.98 (s, 1H), 8.04 (d, 1H), 8.26 (d, 1H)

< Dye D42 >



[0078] NMR (1H, DMSO): 1.04 (t, 6H), 1.78 (s, 6H), 3.42 (q, 4H), 4.04 (s, 3H), 6.04 (s, 1H), 6.92 (d, 1H), 7.40 (d, 1H), 7.70 (d, 1H), 7.82 (d, 1H), 7.88 (d, 2H), 8.04 (s, 1H), 8.06 (d, 2H), 8.26 (d, 1H), 8.36 (d, 1H)

Table 1

Example	Dye	λ_{\max}	Tm (°C)	Td (°C)	Rtop	Jitter (%)	I14/I14H
Example 1	D1	585	225	243	-	-	-
Example 2	D2	591	-	234	56	10	65
Example 3	D3	587	198	233	54	9	68
Example 4	D4	593	241	246	53	7.0	72
Example 5	D5	622	-	216	-	-	-
Example 6	D6	613	-	218	46	8.5	67
Example 7	D7	615	193	231	47	8.0	69
Example 8	D8	614	-	249	46	7.6	65
Example 9	D9	584	146	225	-	-	-
Example 10	D10	591	-	238	-	-	-

Table 1 (continued)

Example	Dye	λ_{\max}	T _m (°C)	T _d (°C)	R _{top}	Jitter (%)	I14/I14H
Example 11	D11	590	212	217	-	-	-
Example 12	D12	590	-	238	-	-	-
Example 13	D13	579	154	218	-	-	-
Example 14	D14	588	198	241	-	-	-
Example 15	D15	590	160	206	56	13	61
Example 16	D16	609	223	230	52	14	60
Example 17	D17	590	247	250	54	9.0	65
Example 18	D18	588	219	231	57	8.1	67
Example 19	D19	594	223	238	54	11	60
Example 20	D20	595	223	238	53	11	63
Example 21	D21	594	192	255	55	10	60
Example 22	D22	640	-	278	-	-	-
Example 23	D23	630	191	232	-	-	-
Example 24	D24	629	220	227	-	-	-
Example 25	D25	631	172	237	-	-	-
Example 26	D26	601	-	255	50	13	52
Example 27	D27	598	-	255	48	9.0	60
Example 28	D28	607	188	214	46	12	55
Example 29	D29	602	-	210	47	8.5	63
Example 30	D30	601	-	207	48	12	57
Example 31	D31	603	159	229	49	13	57
Example 32	D32	600	231	243	49	8.0	61
Example 33	D33	598	-	230	50	8.3	62
Example 34	D34	538	-	241	-	-	-
Example 35	D35	539	209	232	-	-	-
Example 36	D36	542	109	234	-	-	-
Example 37	D37	523	-	225	-	-	-
Example 38	D38	519	-	219	-	-	-
Example 39	D39	518	-	226	-	-	-
Example 40	D40	518	-	256	-	-	-
Example 41	D41	588	234	245	-	-	-
Example 42	D42	573	-	163	-	-	-

[0079] As shown in Table 1, the recording characteristics, including jitter, of the optical disks of Examples 1 through 42, which were evaluated using the DVD-R recorder, are excellent. Also, the reproduction characteristics of the optical disks of Examples 1 through 42, evaluated with the DVD player, ensures that the optical disks are compatible with DVD players.


[0080] As previously mentioned, the novel hemicyanine dye having formula (1) above is easy to synthesize with high yield. Thus, use of the hemicyanine dye as an optical recording material in manufacturing optical recording media can reduce the manufacturing cost, compared to when a conventional optical recording material is adopted.

[0081] While this invention has been particularly shown and described with reference to preferred embodiments

thereof, it will be understood by those skilled in the art that various changes in form and details may be made thereto without departing from the spirit and scope of the invention as defined by the appended claims.


Claims

1. A hemicyanine dye having formula (1):




where Z is a benzene ring, naphthalene ring or anthracene ring; X_1 is S, O, Se, NR or $C(CH_3)_2$, where R is hydrogen or an alkyl group of 1 to 5 carbon atoms; R_1 is hydrogen, a halogen atom, an alkyl group of 1 to 3 carbon atoms, a nitro group, an alkoxy group of 1 to 3 carbon atoms or an amine group; each of R_2 and R_4 is an alkyl group of 1 to 5 carbon atoms; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; Y is Cl, Br, I, ClO_4 , BF_4 , BrO_4 , PF_6 , CH_3SO_3 , CF_3SO_3 , $4-CH_3C_6H_4SO_3$, $C_6H_5SO_3$, $6-SO_3C_{10}H_6SO_3$ or HSO_4 ; and n is an integer of 0-2.

2. The hemicyanine dye of claim 1, wherein the hemicyanine dye having formula (1) is a compound having formula (2) or (3):




where R_1 is H, NO_2 or Cl; R_2 is CH_3 , C_2H_5 , C_3H_7 or C_4H_9 ; X_1 is $C(CH_3)_2$ or S; R_3 is H, OH, $OCOCH_3$ or $OSO_2C_6H_4Cl$; R_4 is C_2H_5 , C_3H_7 or C_4H_9 ; and Y is ClO_4 , BF_4 , PF_6 , I, Br or Cl, and




where X_1 is $C(CH_3)_2$; R_2 is CH_3 , C_2H_5 , C_3H_7 or C_4H_9 ; R_3 is H or OH; R_4 is C_2H_5 , C_3H_7 or C_4H_9 ; and Y is ClO_4 , BF_4 , PF_6 , I, Br or Cl.

3. An optical recording medium comprising a transparent substrate with grooves, a recording layer including a laser absorptive dye, formed over the transparent substrate, and a reflective layer and a protective layer formed over the recording layer, wherein the dye of the recording layer is a hemicyanine dye according to claim 1 or 2.
4. The optical recording medium according to claim 3, wherein the hemicyanine dye shows a maximum absorption in the wavelength range of 350-650 nm, and has a reflective index of 1.8-2.3 in the wavelength range of 400-700 nm.
5. The optical recording medium according to claim 3 or 4, wherein the substrate has a transmittance of 70-99%, and a thickness of 0.01-10 mm.
6. The optical recording medium according to claim 5, wherein the substrate has a transmittance of about 90%.

FIG. 1





(19)

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 156 084 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
13.08.2003 Bulletin 2003/33

(51) Int Cl.7: **C09B 23/14**, C09B 23/10,
G11B 7/24

(43) Date of publication A2:
21.11.2001 Bulletin 2001/47

(21) Application number: **01302847.7**

(22) Date of filing: **27.03.2001**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**
Designated Extension States:
AL LT LV MK RO SI

- Huh, Young-jae
Seongnam-city, Kyungki-do (KR)
- Lee, Kyu-youn
Seocho-gu, Seoul (KR)

(30) Priority: **17.05.2000 KR 2647000004**


(71) Applicant: **SAMSUNG ELECTRONICS CO., LTD.**
Suwon-City, Kyungki-do (KR)

(74) Representative: **Kyle, Diana**
Elkington and Fife
Prospect House
8 Pembroke Road
Sevenoaks, Kent TN13 1XR (GB)

(72) Inventors:
• Je, Jong-tae
Gangnam-gu, Seoul (KR)

(54) **Hemicyanine dyes and optical recording media using the same**

(57) A hemicyanine dye having formula (1), and an optical recording medium using the hemicyanine dye as an optical recording medium are provided:



...(1)

where Z is a benzene ring, naphthalene ring or anthracene ring; X₁ is S, O, Se, NR or C(CH₃)₂, where R is hydrogen or an alkyl group of 1 to 5 carbon atoms; R₁ is hydrogen, a halogen atom, an alkyl group of 1 to 3 carbon atoms, a nitro group, an alkoxy group of 1 to 3 carbon atoms or an amine group; each of R₂ and R₄ is an alkyl group of 1 to 5 carbon atoms; R₃ is H, OH, OCOCH₃ or OSO₂C₆H₄Cl; Y is Cl, Br, I, ClO₄, BF₄, BrO₄, PF₆, CH₃SO₃, CF₃SO₃, 4-CH₃C₆H₄SO₃, C₆H₅SO₃, 6-SO₃C₁₀H₆SO₃ or HSO₄; and n is an integer of 0-2. The hemicyanine dye having formula (1) above is easy to synthesize with high yield. Thus, use of the hemicyanine dye as an optical recording material in manufacturing optical recording media can reduce the manufacturing cost.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 30 2847

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	GB 2 329 751 A (FUJI ELECTRIC CO LTD) 31 March 1999 (1999-03-31) * compounds I-1, I-2, I-4, I-16 * * page 14, line 1 - line 13; claims; figure 5 * * page 15, last paragraph *	1-6	C09B23/14 C09B23/10 G11B7/24
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 11, 30 September 1998 (1998-09-30) & JP 10 151854 A (MITSUI CHEM INC), 9 June 1998 (1998-06-09) * paragraphs 15, 23, 30; formulae (A), (C), (D) * * abstract *	1-6	
X	PATENT ABSTRACTS OF JAPAN vol. 1999, no. 09, 30 July 1999 (1999-07-30) & JP 11 106413 A (SHOWA DENKO KK), 20 April 1999 (1999-04-20) * page 6, formulae 3, 5 * * abstract *	1,2	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C09B G11B
X	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 01, 28 February 1995 (1995-02-28) & JP 06 295150 A (TOYO INK MFG CO LTD), 21 October 1994 (1994-10-21) * page 9, formula 3 * * abstract *	1	
		-/--	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19 June 2003	Examiner Ginoux, C
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 03 82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 01 30 2847

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
P, X	WO 01 19923 A (HAYASHIBARA BIOCHEM LAB ;KASADA CHIAKI (JP); KAWATA TOSHIO (JP); D) 22 March 2001 (2001-03-22) * formulae, 1,2,4,15,16,19,31-33,44,51, 52,55; claims * & EP 1 130 063 A 5 September 2001 (2001-09-05) ---	1-6	
X	S.METSOV ET AL.: "Infrared and NMR study of some 2-styrylindolium dyes" JOURNAL OF MOLECULAR STRUCTURE., vol. 350, no. 3, 15 May 1995 (1995-05-15), pages 241-6, XP002244633 ELSEVIER, AMSTERDAM., NL ISSN: 0022-2860 compounds 2j, 2k, 4b -----	1,2	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19 June 2003	Examiner Ginoux, C
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1503 03/82 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 2847

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

19-06-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2329751 A	31-03-1999	JP 3257470 B2	18-02-2002
		JP 11099746 A	13-04-1999
		JP 11099747 A	13-04-1999
		US 6103331 A	15-08-2000
JP 10151854 A	09-06-1998	NONE	
JP 11106413 A	20-04-1999	NONE	
JP 06295150 A	21-10-1994	JP 6295151 A	21-10-1994
WO 0119923 A	22-03-2001	EP 1130063 A1	05-09-2001
		WO 0119923 A1	22-03-2001

EPO FORM P0456

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82